

Refractive Indices		SF5
	λ [nm]	
$n_{2325.4}$	2325.4	
$n_{1970.1}$	1970.1	
$n_{1529.6}$	1529.6	
$n_{1060.0}$	1060.0	1.65106
n_t	1014.0	1.65208
n_s	852.1	1.65665
n_r	706.5	1.66328
n_C	656.3	1.66661
$n_{C'}$	643.8	1.66756
$n_{632.8}$	632.8	1.66846
n_D	589.3	1.67252
n_d	587.6	1.67270
n_e	546.1	1.67764
n_F	486.1	1.68750
$n_{F'}$	480.0	1.68876
n_g	435.8	1.69985
n_h	404.7	1.71068
n_i	365.0	1.73055

Constants of Dispersion Formula	
A_0	2.7105646
A_1	$-9.1211994 \cdot 10^{-3}$
A_2	$2.7760538 \cdot 10^{-2}$
A_3	$1.2739656 \cdot 10^{-3}$
A_4	$-4.7889342 \cdot 10^{-5}$
A_5	$8.0562028 \cdot 10^{-6}$