

Refractive Indices		SF59
	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	
$n_{1970.1}$	1970.1	
$n_{1529.6}$	1529.6	
$n_{1060.0}$	1060.0	1.90784
$n_t$	1014.0	1.90975
$n_s$	852.1	1.91865
$n_r$	706.5	1.93221
$n_c$	656.3	1.93928
$n_{c'}$	643.8	1.94132
$n_{632.8}$	632.8	1.94325
$n_D$	589.3	1.95210
$n_d$	587.6	1.95250
$n_e$	546.1	1.96349
$n_F$	486.1	1.98605
$n_{F'}$	480.0	1.98900
$n_g$	435.8	2.01559
$n_h$	404.7	2.04279
$n_i$	365.0	

Constants of Dispersion Formula	
$A_0$	3.6049456
$A_1$	$-1.7579501 \cdot 10^{-2}$
$A_2$	$5.4777275 \cdot 10^{-2}$
$A_3$	$8.0837909 \cdot 10^{-3}$
$A_4$	$-7.6975589 \cdot 10^{-4}$
$A_5$	$7.9262505 \cdot 10^{-5}$